

Product	MgO (%)	SiO₂ (%)	CaO (%)	Al₂O₃ (%)	Fe₂O₃ (%)	Loss on ignition (%)	Particle size
Dead burned magnesite 9003	90,00	4,50	2,50	1,50	1,50	1,00	0 - 3 mm (< 1 mm: 55,00%)
Dead burned magnesite 9010	90,00	4,50	2,50	1,50	1,50	0,60	0 - 10 mm (< 1 mm: 10,00 %)
Magnesium oxide TA-3	91,50	3,2	1,85	1,00	1,25	0,95	60,00% < 63 μm/ 250 mesh
Magnesium oxide TA-6	89,50	7,00	3,50	0,50	0,50	0,50	60,00% < 63 μm/ 250 mesh
Dead burned magnesite Extra	96,50	1,00	2,00	0,10	0,60	0,20	0 - 15 mm (< 1 mm: 10,00%)