

Grade	Substance	Al₂O₃ (%)	CaO (%)	SiO₂ (%)	Mohs Hardness
LUVOGRIP	Corundum	65.18	0.90	5.97	8.5
LUVOGRIP BRITE	Mineral aggregates	8.00	45.00	36.00	7.5